
## BELCOM



# One and Done Solution

Today, wood remains one of the most attractive and cost effective choices for construction projects. Belco's preservative treated XT Post is leading the charge. With a 20-year limited warranty, XT Post products not only provide you with a beautiful, single step solution for post installation but also longlasting peace of mind.







Manufactured by Belco Forest Products P: 360.426.8900 | belcofp.com

### BELCO XT® POST

#### PRESERVATIVE TREATMENT - WOLMAN® AG

- ▲ A water-based, nonmetallic, wood preservative surface treatment
- Wolman® AG is an EPA approved treatment

#### **FUNCTIONAL**

■ Structural engineered columns provide greater stability, less warp, and reduced potential for checking than solid timber or hollow posts

#### **COST EFFECTIVE**

- № Pre-primed, trimmed out post saves time and money during installation — no more column wrapping
- Metal free, non-corrosive treatment means no special tools or fasteners
- ★ Less costly than fiberglass or aluminum alternatives

 4x4 XT Post
 8x8 XT Post

 Net: 3-1/2" x 3-1/2"
 Net: 7" x 7-1/4"

 Lengths: 10', 12'
 Lengths: 10', 12'

 Texture: Combed
 Texture: Combed

 6x6 XT Post
 4x6 XT Post

 Net: 5 x 5 1/2
 Net: 3 x 5

 Lengths: 8', 10', 12'
 Lengths: 12

Texture: Combed Texture: Combed

#### **IDEAL FOR:**

- Porch posts
- Rail posts
- **W** Gazebos
- M Corbels



## **EXTERIOR POST PRODUCT**

#### Allowable Axial Load Capacities

	4X4			6X6			8X8		
Column Length (ft)	C <sub>D</sub> =1.0	$C_{D} = 1.15$	C <sub>D</sub> =1.25	C <sub>D</sub> =1.0	$C_{D} = 1.15$	$C_{D} = 1.25$	C <sub>D</sub> =1.0	$C_{D} = 1.15$	$C_{D} = 1.25$
	2452	2820	3065	9774	11240	12217	19239	22125	24049
10	1695	1950	2119	8405	9666	10507	18333	21083	22916
	1212	1393	1515	6678	7679	8347	16790	19309	20988

- 1 All allowable load capacities are determined for compression only in accordance with the Design Values as published in the APA Product Report PR-L321. Allowable load capcities assume dry use, untreated applications in sustained exposure of temperatures < 100°F (38°C).
- 2 For wet service conditions the allowable axial capacity should be multiplied by CM = 0.73.
- 3 For service conditions above 100°F (38°C), the allowable axial capacity should be multiplied by the appropriate Ct factor in Table 2.3.3 of the National Design Specification for Wood Construction.
- 4 Table assumes that effective column length is equal to actual column length and end conditions are rotation free, translation fixed.

#### **INSTALLING**

#### **UPLIFT APPLICATION**

When Belco XT Post has been designed for use in an uplift application, post bases and caps are REQUIRED. Belco recommends Simpson Strong Tie products but products of equal properties are accepted. Refer to base and cap manufacturer's instructions for capacities and connector attachment.

## VERTICAL LOAD ONLY APPLICATION

When Belco XT Post has been designed for use in a vertical load only application, a nailed connection can be implemented.

Raised Base Connection Connection Connection